



Technical Data Sheet

Quality Specification

Testliner 1

	Basis Weigth	Bursting Strength	Burst Index	SCT, CD	SCT, CD
Dimension	[g/m ²]	[kPa]	[kPa m ² /g]	[kN/m]	[kN/m]
Standard	ISO 536	ISO 2759	ISO 2759	ISO 9895	ISO 9895
Tolerance	± 3 %	Minimum per Reel	Minimum per Reel	Average per Delivery	Minimum per Reel
	125	375	3.0	2.6	2.4
	135	405	3.0	2.8	2.6
	170	501	2.95	3.4	3.2
	200	580	2.9	4.0	3.8

Preconditioning: ISO 187, 23°C, 50 % relative humidity

Moisture: 6.5 - 9 %

Sizing: Cobb₆₀ < 35 g/m² on request

Issue date 1 June 2023