



Technical Data Sheet

Quality Specification

Testliner 2

	Basis Weight	Bursting Strength	Burst Index	SCT, CD	SCT, CD
Dimension	[g/m ²]	[kPa]	[kPa m ² /g]	[kN/m]	[kN/m]
Standard	ISO 536	ISO 2759	ISO 2759	ISO 9895	ISO 9895
Tolerance	± 3 % ≤ 200 g/m ² ± 4 % > 200 g/m ²	Minimum per Reel	Minimum per Reel	Average per Delivery	Minimum per Reel
	120	300	2,5	2,09	1,92
	125	313	2,5	2,18	2,00
	130	325	2,5	2,29	2,10
	135	338	2,5	2,30	2,20
	140	350	2,5	2,40	2,25
	150	375	2,5	2,55	2,40
	160	400	2,5	2,72	2,60
	170	425	2,5	2,90	2,75

Preconditioning: ISO 187, 23°C, 50 % relative humidity

Moisture: 6.5 - 9 %

Sizing: Cobb₆₀ < 35 g/m² on request

Issue date 1 January 2023